

*Technical Data Sheet*

---

**CPS 3010 G:**

CPS 3010 G is a fully formulated UV curable ink jet resin

**Handling and Storage:**

CPS 3010 G is stable for up to 6 months at ambient conditions.

Refrigeration will improve shelf life. Elevated temperatures will decrease shelf life.

This product is light sensitive and should not be exposed to daylight, UV light and artificial lighting during storage. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during handling.

**General information:**

CPS 3010 G is an ink jet formulation with excellent durability, high hardness, and adhesion to glass, steel, and aluminum. Cures rapidly with UV broadband or LED light with low oxygen inhibition.

**Physical Properties:**

Adhesion to Glass, Steel, Aluminum	ASTM D3359-09	5
Tensile Modulus Strength Elongation	ASTM D638-10	685 MPa
		20 MPa
		9 %
Shore D Hardness	ASTM D2240-15	76 D
Viscosity		12 cps @ 25 C

**Arkema Inc., 3D Printing Development Center**  
1880 S. Flatiron Ct STE J, Boulder, CO 80301

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/>

Arkema - a French société anonyme, registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790

**arkema.com**

